

DUPONT™ STONETECH® PROFESSIONAL ENHANCER

TECHNICAL DATA SHEET



PROTECT

CLEAN

TRANSFORM

PRODUCT BENEFITS

- Enriches color
- Standard protection against most stains
- Easy to use, water-based formula
- Interior use

RECOMMENDED SURFACES

Unpolished natural stone such as bluestone, flagstone, travertine, limestone, slate, textured stone, flamed stone and tumbled stone.

Grout, masonry and concrete.

AVAILABLE SIZES

Quart, Gallon, 5 Gallon

COVERAGE

Up to 250 sq ft per gallon.

EXPECTED WEAR

Up to 5 years on interior surfaces.

TECHNICAL INFORMATION

Form:	Liquid
Specific Gravity:	0.983
HMIS Rating:	2,1,0
Flash Point:	>230 °F (110 °C)
Freeze Point:	32 °F (0 °C)
pH:	4.5

VOC CONTENT

<400 g/L (excluding water) for EPA purposes.

<120 g/L (including water) for U.S. state purposes (Low Solids Coating).

DIRECTIONS

Read entire label before using. Use only as directed. Test in a small inconspicuous area with a 24-hour cure time to determine ease of application and desired results. Allow new grout installations to cure for at least 72 hours prior to application. Be sure surface is clean, thoroughly dry and free of sealers, waxes and coatings. Not recommended for exterior surfaces. Avoid skin and eye contact. Wear protective eyewear and gloves. Ensure work area is well-ventilated during application and until surface is dry. Keep children and pets out of the area during application and drying.

1. Shake well before using.
2. Apply product evenly and liberally using a paint pad, low-pressure chemical-resistant sprayer, roller or brush. Avoid applying product on unintended surfaces.
3. Allow product to penetrate the surface for 15–30 minutes; denser material may require maximum time for Enhancer to penetrate. Spread excess sealer over entire area for even penetration. Following penetration time, completely wipe surface dry with a clean dry towel. **DO NOT ALLOW EXCESS ENHANCER TO DRY COMPLETELY ON SURFACE.**
4. A second coat may be needed for porous, absorbent surfaces or if a darker appearance is required. Apply second coat 1 hour after first coat following directions in steps 1–3.
5. A full cure is achieved after 24–72 hours; foot traffic may begin in 6–8 hours. If needed sooner, cover the floor with red rosin paper to protect it until the recommended time periods have passed.
6. Clean tools used during application with water.

STORAGE AND HANDLING INSTRUCTIONS

CAUTION: HARMFUL IF SWALLOWED. MAY CAUSE EYE, SKIN AND RESPIRATORY IRRITATION. Do not ingest. Avoid contact with eyes and skin. Avoid prolonged exposure to vapors. **KEEP OUT OF THE REACH OF CHILDREN.** Do not freeze or store above 100 °F/38 °C. Do not mix with other chemicals. Do not release to waterways.

EMERGENCY/FIRST AID PROCEDURES

Ingestion: Do not induce vomiting. Call poison control center. Call a physician immediately.

Eye Contact: Flush thoroughly with water for at least 15 minutes. Call a physician if eye irritation persists.

Skin Contact: Wash skin with mild soap and water. Call a physician if skin irritation persists. Launder affected clothing before re-wearing.

Inhalation: Remove affected person to fresh air. Call a physician if respiratory irritation persists.

The DuPont™ StoneTech® Professional product line complies with all federal, state and local VOC regulatory requirements.

DuPont™ StoneTech® Professional
2520 Barrington Court
Hayward, CA 94545

Technical Support: 888-786-6343
Customer Service: 877-786-6383

www.stonetechpro.com



The miracles of science™

The information is furnished free of charge and based on information that DuPont believes to be generally reliable and accurate. Individual facts and circumstances may differ. It is intended for your use at your own risk. Because conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information.

Copyright © 2014 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, and StoneTech® are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

K-20518-1 (03/14)